

(A)
Cont,

by weight [, preferably from 20 to 50% by weight, in each case] based on the total weight of the polyester urethane.

6. (Amended) The film as claimed in [one or more of claims 1 to 5] claim 1, wherein the thermoplastic mixture comprises at least one plasticizer, [preferably glycerol, diglycerol, sorbitol, polyethylene glycol, triethyl citrate, triethyl acetyl citrate, glycerol triacetate, a phthalic ester or sorbitol monoester or sorbitol diester,] the proportion of plasticizer(s) being up to 40% by weight [, preferably up to 25% by weight, in each case] based on the total weight of the thermoplastic mixture.
7. (Amended) The film as claimed in [one or more of claims 1 to 6] claim 1, wherein the thermoplastic mixture comprises at least one lubricant, [preferably a vegetable fat or a vegetable oil, a synthetic triglyceride, lecithin, an ethoxylated fatty alcohol or a wax,] the proportion of lubricant(s) being up to 12% by weight [, preferably from 0.1 to 6% by weight, particularly preferably from 0.2 to 6% by weight, in each case] based on the total weight of the thermoplastic mixture.
8. (Amended) The film as claimed in [one or more of claims 1 to 7] claim 1, wherein the thermoplastic mixture is mixed with fibers, [preferably fibers from cotton linters, woodpulp, from regenerated cellulose, from hemp, flax, sisal or jute,] the proportion of fibers being up to 30% by weight [,preferably from 2 to 15, particularly preferably from 5 to 15% by weight, in each case] based on the total weight of the mixture.
9. (Amended) The film as claimed in [one or more of claims 1 to 8] claim 1, wherein the thermoplastic mixture comprises fillers, [preferably calcium carbonate, talc, kaolin, titanium dioxide, anhydrite, a silicate or fine-grained cellulose particles or starch particles] the proportion of the fillers being up to 30%.

A1
CONT

by weight [, preferably from 2 to 15% by weight, particularly preferably from 4 to 10% by weight, in each case] based on the total weight of the mixture.

10. (Amended) The film as claimed in [one or more of claims 1 to 9] claim 1, wherein the thermoplastic mixture comprises at least one crosslinker, [preferably a dicarboxylic acid, a diisocyanate or triisocyanate, a dialdehyde, a diepoxide, a diimine, or a silane or siloxane containing vinyl group(s),] the proportion of crosslinker(s) being up to 10% by weight [, preferably from 0.5 to 5% by weight, particularly preferably from 1 to 3% by weight, in each case] based on the total weight of the mixture.

11. (Amended) The film as claimed in [one or more of claims 1 to 10] claim 1, wherein it is hot-sealable.

12. (Amended) The film as claimed in [one or more of claims 1 to 11] claim 1, wherein it is furnished with an inner and/or outer preparation.

13. (Amended) A process for producing a film as claimed in [one or more of claims 1 to 12] claim 1, which comprises blowing the tube which is produced from the thermoplastic mixture by extrusion, the area-based drawing ratio being in the range from 2 to 70 [, preferably from 4 to 40, particularly preferably from 6 to 20].

14. (Amended) The use of the film as claimed in [one or more of claims 1 to 12] claim 1 as packaging film [, in particular for foods, preferably as seamless, tubular sausage casing].

Please add the following new claim:

--15. The use of the film as claimed in claim 1 as seamless, tubular sausage casing.--